

**QUICKSILVER®**  
Premium Truck Liner



*The world of plastics at your door.*

Phone 905-563-0226 • Toll Free 1-800-642-7797 • Fax 905-563-0228  
www.polyzone.com

## PHYSICAL PROPERTIES

QuickSilver® high performance dump truck liners are designed to clean-out and clean-up of some of the toughest materials including hot asphalt in the very worst conditions. From winter freeze to summer heat, QuickSilver® truck liners release sticky materials, meaning faster load release, less equipment damage, reduced chance of tip-over, less wear on hoists, minimal clean-up and reduced downtime. On-road, off-road or heavy equipment, we've got a QuickSilver® liner for you. Quicksilver® will handle any temperature asphalt, which at the high end is usually 400°F.

Property	Method	Unit	Nominal Value*
Density	ASTM D-792	lbs/ft3	0.93
Tensile strength at yield	ASTM D-638	psi	2711
Tensile modulus	ASTM D-638	psi	94,395
Elongation at yield	ASTM D-638	%	n/a
Elongation at break	ASTM D-638	%	201
Tensile impact	DIN 53448	ft-lbs/in2	1048
Flexural modulus	ASTM D-790	psi	103,095
Flexural strength	ASTM D-790	psi	n/a
Izod impact	ASTM D-4020	ft-lbs/in2	25
IZOD impact notched	ASTM D-2240	ft-lbs/in2	n/a
Compressive modulus	ASTM D-695	psi	n/a
Compressive deformation	ASTM D-621	% at 1000 psi	6.0 - 8.0
Hardness	ASTM D-2240	Shore D	66
Static friction	ASTM D-1894	Unitless	0.14
Dynamic friction	ASTM D-1894	Unitless	0.1
Melting point	ASTM D-3417	°F	280
Coefficient of linear thermal expansion	ASTM D-696	°F-1	0.00011
Max. operating temp.		°F	180
Volume Resistivity	ASTM D-257	Ohm-cm	>10 <sup>15</sup>
Surface Resistivity	ASTM D-257	Ohm	>10 <sup>15</sup>
Water absorption 24hrs.	ASTM D-570	%	nil

\*All values are determined on specimens prepared according to ASTM 1248-84 "Standard Specifications for Polyethylene Plastic Molding and Extrusion Materials". Nominal values should not be interpreted as specifications.

**NOTICE:** All statements, information, and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representations or warranty that such use is free of patent infringement and are not recommendations to infringe any patent.

