

ACRYLITE®
Sign White Acrylic

plastruct  polyzone

The world of plastics at your door.

Phone 905-563-0226 • Toll Free 1-800-642-7797 • Fax 905-563-0228
www.polyzone.com

PHYSICAL PROPERTIES

ACRYLITE® sign white acrylic sheet is the highest quality continuously manufactured sheet on the market today. Using a proprietary, innovative process, ACRYLITE® sheet products are economical, provide tight thickness tolerance, high optical characteristics and low stress levels.

Property	Method	Unit	Nominal Value*
Density	ASTM D-792	g/cm ³	1.19
Tensile strength at yield	ASTM D-638	psi	10,300
Tensile modulus	ASTM D-638	psi	400,000
Elongation at yield	ASTM D-638	%	4.5
Elongation at break	ASTM D-638	%	n/a
Tensile impact	DIN 53448	ft-lbs/in ²	n/a
Flexural modulus	ASTM D-790	psi	480,000
IZOD impact notched	ASTM D-2240	ft-lbs/in ²	0.4
Hardness	ASTM D-2583	Barcol	48
Melting point	ASTM D-3417	°F	n/a
Coefficient of linear thermal expansion	ASTM D-696	in/in/°F	2.8 x 10 ⁻⁵
Heat deflection temperature, 264 psi	ASTM D-648	°F	195
Vicat softening temperature	ASTM D-1525	°F	230
Max. operating temp.		°F	160
Volume Resistivity	ASTM D-257	Ohm-cm	>10 ¹⁶
Surface Resistivity	ASTM D-257	Ohm	>10 ¹⁵
Water absorption 24hrs.	ASTM D-570	%	0.2
Smoke density, 0.125"	ASTM D-2843	%	5.0 - 10.0
Self-ignition temperature	ASTM D-1929	°F	830
Flammability 0.125"	ASTM D-635	in/min.	1
Light transmission, Clear	ASTM D-1003	%	92
Light transmission, Sign White 015-2	ASTM D-1003	%	30
Light transmission, Bronze 126-4	ASTM D-1003	%	45
Haze	ASTM D-1003	%	1.6
Refractive index	ASTM D-542		1.49

*All values are determined on specimens prepared according to ASTM 1248-84 "Standard Specifications for Polyethylene Plastic Molding and Extrusion Materials". Nominal values should not be interpreted as specifications.

NOTICE: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representations or warranty that such use is free of patent infringement and are not recommendations to infringe any patent.

