

## NYLATRON MC901, PA6, Heat Stab.



The world of plastics at your door.

Phone 905-563-0226 • Toll Free 1-800-642-7797 • Fax 905-563-0228  
www.polyzone.com

## PHYSICAL PROPERTIES

Nylatron MC901 is a heat stabilized formula designed to improve the mechanical, thermal and bearing properties of type 6 cast nylon while maintaining its basic electrical and chemical characteristics. The added heat stabilization also contributes dramatically to component service life, making Nylatron MC901 an excellent choice. Nylatron MC901 nylon offers great wear resistance, low surface friction, high strength and great rigidity

Property	Method	Unit	Nominal Value*
Density	ASTM D-792	g/cm <sup>3</sup>	1.15
Tensile strength at yield	ASTM D-638	psi	12,000
Tensile modulus	ASTM D-638	psi	400,000
Elongation at yield	ASTM D-638	%	n/a
Elongation at break	ASTM D-638	%	20
Tensile impact	DIN 53448	ft-lbs/in <sup>2</sup>	n/a
Flexural modulus	ASTM D-790	psi	500,000
Flexural strength	ASTM D-790	psi	16,000
Izod impact	ASTM D-4020	ft-lbs/in <sup>2</sup>	n/a
IZOD impact notched	ASTM D-2240	ft-lbs/in <sup>2</sup>	0.4
Compressive modulus	ASTM D-695	psi	400,000
Compressive deformation	ASTM D-695	1% at 1000 psi	n/a
Hardness	ASTM D-2240	Shore D	85
Melting point	ASTM D-3417	°F	420
Coefficient of linear thermal expansion	ASTM D-696	in/in/°F	4.5 x 10 <sup>-5</sup>
Heat deflection temperature, 264 psi	ASTM D-648	°F	200
Vicat softening temperature	ASTM D-1525	°F	n/a
Max. operating temp. (Air)		°F	260
Volume Resistivity	ASTM D-257	Ohm-cm	n/a
Surface Resistivity	ASTM D-257	Ohm	>10 <sup>13</sup>
Water absorption 24hrs.	ASTM D-570	%	n/a
Water absorption, Saturation	ASTM D-570	%	n/a

\*All values are determined on specimens prepared according to ASTM 1248-84 "Standard Specifications for Polyethylene Plastic Molding and Extrusion Materials". Nominal values should not be interpreted as specifications.

**NOTICE:** All statements, information, and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representations or warranty that such use is free of patent infringement and are not recommendations to infringe any patent.

