

**TIVAR 1000®****(UHMW) Ultra High Molecular Weight Polyethylene****plastruct  polyzone***The world of plastics at your door.*Phone 905-563-0226 • Toll Free 1-800-642-7797 • Fax 905-563-0228  
www.polyzone.com**PHYSICAL PROPERTIES**

TIVAR 1000® is superior ultra high molecular weight sheet that is extremely tough as well as incredibly abrasion resistant. With very low co-efficient of friction, this material is best used in rough duty applications. As with most plastics, care must be taken when machining to ensure dimensional stability is maintained. Typical applications for Tivar 1000® include; most wear applications, bearings, bushings, pipe saddles, conveyor guides and numerous others. Various modified forms are also used to broaden the scope of applications.

Property	Method	Unit	Nominal Value*
Density	ASTM D-792	lbs/ft <sup>3</sup>	0.93
Tensile strength at yield	ASTM D-638	psi	3050
Tensile modulus	ASTM D-638	psi	120,000
Elongation at yield	ASTM D-638	%	n/a
Elongation at break	ASTM D-638	%	200
Tensile impact	DIN 53448	ft-lbs/in <sup>2</sup>	715
Flexural modulus	ASTM D-790	psi	110,000
Flexural strength	ASTM D-790	psi	n/a
Izod impact	ASTM D-4020	ft-lbs/in <sup>2</sup>	no break
IZOD impact notched	ASTM D-2240	ft-lbs/in <sup>2</sup>	n/a
Compressive modulus	ASTM D-695	psi	77,750
Compressive deformation	ASTM D-621	% at 1000 psi	6.0 - 8.0
Hardness	ASTM D-2240	Shore D	68
Static friction	ASTM D-1894	Unitless	0.21
Dynamic friction	ASTM D-1894	Unitless	0.14
Melting point	ASTM D-3417	°F	280
Coefficient of linear thermal expansion	ASTM D-696	°F-1	0.00011
Max. operating temp.		°F	180
Volume Resistivity	ASTM D-257	Ohm-cm	>10 <sup>15</sup>
Surface Resistivity	ASTM D-257	Ohm	>10 <sup>15</sup>
Water absorption 24hrs.	ASTM D-570	%	nil

\*All values are determined on specimens prepared according to ASTM 1248-84 "Standard Specifications for Polyethylene Plastic Molding and Extrusion Materials". Nominal values should not be interpreted as specifications.

NOTICE: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representations or warranty that such use is free of patent infringement and are not recommendations to infringe any patent.

